



# CONSTRUCTION AND MAINTENANCE PRODUCTS FOR BUILDING

Foundation Coating

P-60

## Description

P-60 is an asphalt based foundation coating used to waterproof concrete and masonry foundation. It seals leaks and maintains watertightness.

## Surface Preparation

Avoid use if rain is forecast. Surface must be clean and free of all loose or foreign materials. At first on a new foundation, seal the joint between footing and foundation wall with a bead of plastic cement P-20, P-25 or P-2000. To fill holes, cracks and weak spots ; use the same product. To ease application in cold season, keep the product in a warm place. Stir well before use. Apply product with a paintbrush, roller or sprayer. Close container after each use. Clean tools with mineral spirits. EXTERIOR USE ONLY.

## Norm

CAN/O.N.G..C. 37-GP-6MA

## Package

Offer in 3.78L and 18.9L pail.

## Shelf Life

This product can be kept in its original container, hermetically closed for 1 year from date of purchase.





# CONSTRUCTION AND MAINTENANCE PRODUCTS FOR BUILDING

Foundation Coating

P-60

## Technical Data Table

|                                     |  |
|-------------------------------------|--|
| Color                               | Black  |
| Solids by Volume                    | 65 to 70 %   |
| Weight                              | 0,97 kg/L (8,1 pounds/gal)   |
| Coverage                            | 1 to 2 L/m <sup>2</sup> (2 to 4 gal/100 ft <sup>2</sup> )  |
| Dry Time*                           | To 50 % H.R. 20° C (68° F)   |
| To the Touch*                       | ± 4 hours  |
| Completely Dry*                     | ± 48 hours   |
| Service Temperature                 | -30° C to 95° C (-22 to 203° F)  |
| Application Temperature             | Can be applied at low temperature but preferably above 10° C (50° F). Thickens at low temperature.                                   |
| Chemical Resistance                 | Resistant to water calcium chloride, salt and to lightly acid or alkaline solutions. Is not resistant to oils, greases and solvents. |
| Permeance to Water Vapor (ASTM E96) | 3 mm (1/8 in) coat before drying 2.9 ng/Pa.m <sup>2</sup> .s (0.05 perms)  |

\*Dry Time dependent of surface porosity and temperature.

## Note

Let dry completely before covering or back fill to avoid prematurely product deterioration and leave possibility of humidity infiltration. If product is applied near a ventilation unit or an air conditioner, take necessary precautions to avoid solvent infiltration inside. Protect new work from open flames and adjacent welding activity. Contains petroleum distillates; keep out of reach of children. keep away from open flames, sparks or heat sources. Do not smoke.

## Warranty

The customer shall verify of the suitability of this product for the intended purpose. Applicator's skill, weather and surface conditions being beyond manufacturer's control, we limit our liability to replacement of defective material only in sealed container, within 1 year of proof of purchase. FOB plant.

## Warning



MAY CAUSE IRRITATION.  
CONTENT MAY CATCH FIRE.  
COMBUSTION DANGER  
FIRST AID: Skin contact : Wash skin immediately with soap and water.  
Eye contact : Flush immediately with plenty of water for at least 15 minutes, lifting upper and lower eyelids. Consult a physician.  
Clothes contact : Remove contaminated clothes.  
Inhalation : Move the victim to fresh air. Consult a physician if necessary.  
Ingestion : DO NOT INDUCE VOMITING. Give milk if conscious. Keep victim warm and call immediately a physician.

KEEP OUT OF REACH OF CHILDREN.  
READ SAFETY DATA SHEET BEFORE USING THIS PRODUCT

