



# TECHNICAL DATA

Supply Point: **Montreal, Quebec**

## SEBS 750

CHARACTERISTICS	METHODS	UNITS	SPECIFICATIONS	
			Min	Max
Specific Gravity @ 25°C (77°F)	ASTM D70	g/mL	Report	
Softening Point	ASTM D36	°C (°F)	85 (185)	116 (240)
Softening Point Change After Heat Exposure	ASTM D36	°C (°F)	-5 (-9)	5 (9)
Flash Point, (C.O.C)	ASTM D92	°C (°F)	260 (500)	-
Penetration @ 25°C (77°F) 100g, 5s	ASTM D5	dmm	20	60
Penetration Change After Heat Exposure @ 25°C (77°F) 100g, 5s	ASTM D5	dmm	-5	12
Solubility in Trichloroethylene	ASTM D2042	%	99	-
Low Temperature Flexibility	ASTM D3111	°C (°F)	-	-7 (20)
Tensile Elongation	ASTM D412	%	750	-
Elastic Recovery	ASTM D412	%	80	-

Meets ASTM D6152 - 2011

Date of revision : August 15, 2016  
by : M. Florant