POLYESTER REINFORCEMENT

DESCRIPTION & USE

LEXCOR PR is a saturated and spun-bonded polyester reinforcement mat with starch-based binder, used in various roofing applications, providing exceptional strength and durability.

It can be used:

- with both hot and cold (liquid) applied bitumen coating systems
- as base plies under hot-applied modified bitumen
- · as base flashing for details
- · in multi-ply built-up roofing
- · for roof restoration
- · for roof repairs



Easy application - simply unroll and embed into adhesive

Strong - excellent tear and puncture resistance

Mold resistant - will not absorb moisture or rot

Porous - porosity allows good adhesion between membrane layers

White colour - helps with assuring a good saturation

TECHNICAL DATA

TYPICAL PHYSICAL PROPERTIES			
Property	Unit of Mesure	Typical Value	Test Method
Thickness	mm	1	
Weight	g/m² (osy)	110 (3.8)	ASTM D3776
Elongation MD CD	% @ break	34 36	ASTM D5034
Breaking Force MD CD	N (lbf)	734 (165) 618 (139)	ASTM D5034
Trap Tear Strength MD CD	N (lbf)	160 (36) 147 (33)	ASTM D5733

PACKAGING

- 305 mm x 91.44 m (12" x 300')
- 457 mm x 91.44 m (18" x 300')



INSTALLATION

- In accordance with the manufacturer's recommendations, apply a coat of the hot or cold applied bitumen adhesive on to the substrate.
- Embed reinforcement mat into adhesive immediately, using a brush or broom.
- Ensure the reinforcement mat lies flat without wrinkles, avoiding over-stretching, bridging or "fishmouths".
- Apply a final coat of the hot (liquid) applied bitumen adhesive, in accordance with the manufacturer's recommendations, ensuring the reinforcing mat is not visible.

CAUTIONS & LIMITATIONS

- When using LEXCOR PR with asphaltic materials, do not expose asphaltic materials to the elements (water, solvents, oils or other contaminants that may be harmful)
- · Store rolls upright
- · Store material in a dry place

